

Lack B



Technical Data Sheet

Intended use: Silicone lacquer for coating earmolds and ear impressions

Manufacturer: Dreve Otoplastik GmbH
Max-Planck-Straße 31
59423 Unna / Germany

Composition:

Pos	chemical term
1	polydimethyl siloxane
2	filling materials
3	auxiliaries
4	acetoxysilane vulcanizer in toluene
5	catalyst

Characteristic: Heavy body one component silicone rubber, vulcanizes under the impact of air humidity and splitting of acetic acid to a rubber-elastic resin.

Properties:

Density (unvulcanized): 0.9 - 1 g/cm³ at 23 °C (DIN 53479 A)

Curing: 20 min at 23 °C, 50 - 60% RH

Dreve Otoplastik GmbH

Max-Planck-Str. 31

59423 Unna / Germany

Tel.: 02303 / 8807-0

Fax: 02303 / 82909

info@dreve.de

www.dreve.com